

Little Greene®

— PAINT & PAPER 1773 —

TRADITIONAL OIL PRIMER UNDERCOAT

FORMERLY OIL PRIMER UNDERCOAT

DESCRIPTION

A high opacity combined primer undercoat that is suitable for both wood and metal for interior and exterior applications.

PROPERTIES

Gloss Level	Matt (less than 8%)
Theoretical coverage	16 square meters per litre (varies with surface porosity & texture)
Recommended film thickness	40 microns dry, per coat.
Recommended number of coats	2
Surface dry	4 hours

Time to recoat	16 hours minimum
Volume solids	66%
Colour availability	All Little Greene colour card colours
Pack size availability	1 & 2.5 Litre

APPROVALS & STANDARDS

Manufactured under the auspices of ISO 9001:2008 quality & ISO 14001:2004 environmental management systems.

2004/42/EC EU limit value for this product (cat.A/dsb): 300 g/l (2010). This product contains max.300g/l VOC.

This product has been tested under the regulations outlined in French Indoor Air Quality Decree No 2011-321 – Arrete April 2011 and was awarded an A+.

SURFACE PREPARATION

Hardwood: Not recommended for direct application to resinous hardwoods. Resinous hard woods require cleaning and treatment with Little Greene Aluminium Wood Primer (consult the relevant product data sheets for further details) prior to undercoating.

For non resinous hardwoods, lightly sand just prior to painting for best performance. Seal knots with a proprietary knotting compound.

Softwoods: Lightly sand wood, just prior to painting, for best performance. Seal knots with a proprietary knotting compound.

Ensure moisture content of the timber is below 15% before commencing application. Damp wood should never be painted as this may give rise to blistering, flaking, cracking and premature coating failure.

Green oak should not be painted unless it has been weathered for at least 6 months.

Metals: New ferrous metalwork should be hand, or mechanically cleaned, to remove any surface rust before application of Little Greene Traditional Oil Primer Undercoat. Non ferrous metals must be pre-treated or primed with an appropriate proprietary primer.

Existing paint finish: Remove all loose and flaking paintwork. Degrease with a suitable detergent solution, such as sugar soap, followed by clean water rinse. Rub down thoroughly with a medium grade sand paper to provide a key and a defect free smooth surface, "feathering in" areas where paint has been removed. Make good any repairs, sand and apply primer to exposed surface as appropriate.

Plastics: For long term performance, clean & lightly sand down surfaces, using a proprietary adhesion promoting plastics primer before applying the finishing coat. When item is to be fully encapsulated in the paint (such as external down pipes) then a light rub down is more than adequate.

APPLICATION

Stir thoroughly before use. Do not apply to surfaces when the ambient temperature is below 5°C.

Brushing: Use a high quality natural bristle brush that is suitably sized for the project at hand. New brushes should be conditioned by washing in clean white spirit and thoroughly drying with a clean, lint free, cloth.

Avoid immersing brush too far into the paint to prevent paint from entering the ferrule. Avoid drips and splashes by not overloading the brush. Apply paint in even strokes and only extend painting area such that a wet edge can be easily maintained. For the highest quality appearance, keep final brush strokes all in the same direction and never go over paint that has already begun to dry. Note that some softwoods may require a 5% v/v addition of white spirit to Little Greene Primer Undercoat to ease application.

Roller: Use a short nap mohair type sleeve for best appearance on smooth surfaces. Increase nap length for textured surfaces, as appropriate, to ensure even and thorough coverage. Keep final strokes all in the same direction, maintaining a wet edge throughout. Never be tempted to go over already drying paint as this will lead to lap marking and flashing.

Disclaimer - The information on this data sheet is correct to the best of our knowledge and experience. The Little Greene Paint Company reserves the right to modify data contained herein, without notice. The information supplied does not absolve users from responsibility to carry out their own tests and experiments, nor does it imply any legally binding assurance of certain properties or suitability for any specific purpose. Conditions of service and application may be beyond our control, so no liability whatsoever can be accepted on the basis of the information supplied herein.

The Little Greene Paint Company Limited, Wood Street, Openshaw, Manchester M11 2FB. England.

Tel: 0845 880 5855 (UK) Tel: +44 161 23 00 880 (Overseas) Fax: 0845 880 5877 (UK) Fax: +44 161 22 33 208 (Overseas)

mail@littlegreene.com www.littlegreene.com

Little Greene®

— PAINT & PAPER 1773 —

TRADITIONAL OIL PRIMER UNDERCOAT

FORMERLY OIL PRIMER UNDERCOAT

Spray Finishing:

Conventional

Thin with up to: 25%(v/v) white spirit
Tip size: 1.60 to 2.00 mm (62 to 78 thou)
Air pressure: 0.28 to 0.41 MPa (40 to 60 psi)

Airless

Thin with up to: 10%(v/v) white spirit
Tip size: 0.28 to 0.54 mm (11 to 21 thou)
Pressure at tip: 12.6 to 19.6 MPa (1800 to 2800 psi)

RECOMMENDED FINISHING SYSTEM

Finish with two coats of Little Greene Traditional Oil Gloss or Traditional Oil Eggshell. Additionally, Little Greene Oil Primer Undercoat may alternatively be finished with Little Greene Acrylic Gloss or Little Greene Intelligent Eggshell (consult the relevant product data sheets for further details).

CLEANING

Remove excess paint and clean all equipment using white spirit, or appropriate substitute, immediately after use. Never store brushes or roller sleeves in cleaning solvent as this will result in deterioration of their application performance.

STORAGE & SHELF LIFE

Store unused paint in a cool, dry, frost free area, away from direct sunlight and sources of ignition. Ensure tin lids are securely and correctly replaced after use. When unopened and stored under the conditions above, this product is stable for a minimum period of two years.

DISPOSAL & RECYCLING

Dispose of excess or waste paint via a licensed waste handling operator.
Empty metal containers may be recycled (remove plastic handle on 2.5L tins).

HEALTH & SAFETY

Always read the label on the can before use. Ensure maximum ventilation during application and drying. Consult product material safety data sheet for further details.

Disclaimer - The information on this data sheet is correct to the best of our knowledge and experience. The Little Greene Paint Company reserves the right to modify data contained herein, without notice. The information supplied does not absolve users from responsibility to carry out their own tests and experiments, nor does it imply any legally binding assurance of certain properties or suitability for any specific purpose. Conditions of service and application may be beyond our control, so no liability whatsoever can be accepted on the basis of the information supplied herein.

The Little Greene Paint Company Limited, Wood Street, Openshaw, Manchester M11 2FB. England.

Tel: 0845 880 5855 (UK) Tel: +44 161 23 00 880 (Overseas) Fax: 0845 880 5877 (UK) Fax: +44 161 22 33 208 (Overseas)

mail@littlegreene.com www.littlegreene.com