

Little Greene®

— PAINT & PAPER —

INTELLIGENT PRIMER UNDERCOAT

DESCRIPTION

A high opacity, low odour water based matt undercoat displaying excellent adhesion to existing aged alkyd finishes. Highly recommended for use with Little Greene water based finishes for both internal and external applications.

PROPERTIES

Gloss Level	Matt (less than 6%)
Theoretical coverage	14 square meters per litre (varies with surface porosity & texture)
Recommended film thickness	30 microns dry, per coat.
Recommended number of coats	1 or 2, as required
Surface dry	1 hours

Time to recoat	4 hours minimum
Volume solids	34%
Colour availability	All Little Greene colour card colours
Pack size availability	1 & 2.5 Litre

*The final sheen level may take up to seven days to be reached, depending upon film thickness and drying conditions.

APPROVALS & STANDARDS

Manufactured under the auspices of ISO 9001:2008 quality & ISO 14001:2004 environmental management systems.
BS EN71-3:2013 Safety of toys. Specification for migration of certain elements. (Test certificate available upon request)
2004/42/EC EU limit value for this product (cat.a/dwb): 130g/l (2010). This product contains max.6g/l VOC.

This product has been tested under the regulations outlined in French Indoor Air Quality Decree No 2011-321 – Arrete April 2011 and was awarded an A+.

SURFACE PREPARATION

New wood: For soft woods, knots should be sealed with knotting compound to prevent staining. Resinous hard woods require cleaning and treatment with Little Greene Aluminium Wood Primer (consult the relevant product data sheet for further details) prior to undercoating.

Ensure moisture content of the timber is below 15% before commencing application. Damp wood should never be painted as this may give rise to blistering, flaking, cracking and premature coating failure.

Green oak should not be painted unless it has been weathered for at least 6 months.

Metals: New ferrous metalwork should be hand, or mechanically cleaned, to remove any surface rust before application of Little Greene Traditional Oil Based Primer/Undercoat. Non ferrous metals must be pre-treated or primed with an appropriate proprietary primer.

Existing paint finish: Remove all loose and flaking paintwork. Degrease with a suitable detergent solution, such as sugar soap, followed by clean water rinse. Rub down thoroughly with a medium grade sand paper to provide a key and a defect free smooth surface, "feathering in" areas where paint has been removed. Make good any repairs, sand and apply primer to exposed surface as appropriate.

Plastics: For long term performance, clean & lightly sand down surfaces. Prime using a proprietary adhesion promoting plastics primer before applying Little Greene Intelligent Primer Undercoat.

New plaster walls: For plaster skim, allow at least four weeks for the plaster to thoroughly dry. Apply a primer coat by thinning the paint with a 5 to 25% (v/v) addition of clean water, depending upon the porosity of the substrate. Cut in by brushing at the same dilution recommendation as for priming, to promote flow and sealing of the substrate.

For new, fully plastered walls, allow at least six months for the plaster to thoroughly dry before painting.

This product is not recommended for painting lime or other natural plasters.

Existing plaster walls: Lightly wash any existing paint work to remove any dust or surface laitance. Apply a primer coat by thinning with a 0 to 25% (v/v) addition of clean water, depending upon the porosity of the substrate.

This product is not recommended for painting previously painted lime or other natural plasters.

Disclaimer - The information on this data sheet is correct to the best of our knowledge and experience. The Little Greene Paint Company reserves the right to modify data contained herein, without notice. The information supplied does not absolve users from responsibility to carry out their own tests and experiments, not does it imply any legally binding assurance of certain properties or suitability for any specific purpose. Conditions of service and application may be beyond our control, so no liability whatsoever can be accepted on the basis of the information supplied herein.

The Little Greene Paint Company Limited, The Coach Works, 420 Ashton Old Road, Manchester M11 2DT. England.
Tel: 0845 880 5855 (UK) Tel: +44 161 23 00 880 (Overseas) Fax: 0845 880 5877 (UK) Fax: +44 161 22 33 208 (Overseas)
mail@littlegreene.com www.littlegreene.com

Little Greene®

— PAINT & PAPER —

INTELLIGENT PRIMER UNDERCOAT

APPLICATION

Stir thoroughly before use. Do not apply to surfaces when the ambient temperature is below 5°C or if there is a risk of rain during application or drying. To obtain good flow, apply generously but avoiding runs and sags.

Brushing: Use a high quality synthetic bristle brush that is suitably sized for the project at hand. New brushes should be conditioned by washing in clean water and thoroughly drying with a clean, lint free, cloth.

Avoid immersing brush too far into the paint to prevent paint from entering the ferrule. Avoid drips and splashes by not overloading the brush. Apply paint in even strokes and only extend painting area such that a wet edge can be easily maintained. For the highest quality appearance, keep final brush strokes all in the same direction and never go over paint that has already begun to dry.

For intricate items, or where high ambient temperatures/high air flow conditions cannot be avoided, the open time maybe extended with a 10 to 15% (v/v) addition of a propriety water based paint conditioner. This advice is also applicable to large flat areas; however, use of a paint roller is the recommended application method in such cases.

Roller: Use a short nap wool blend type sleeve for best appearance on smooth surfaces. Increase nap length for textured surfaces, as appropriate, to ensure even and thorough coverage. Keep final strokes all in the same direction, maintaining a wet edge throughout. Never be tempted to go over already drying paint as this will lead to lap marking and flashing. When high ambient temperatures/high air flow conditions cannot be avoided, the open time maybe extended with a 10 to 15% (v/v) addition of propriety water based paint conditioner.

Spray Finishing:

Conventional

Thin with up to: 40%(v/v) water
Tip size: 1.60 to 2.00 mm (62 to 78 thou)
Air pressure: 0.28 to 0.41 MPa (40 to 60 psi)

Airless

Thin with up to: 20%(v/v) water
Tip size: 0.28 to 0.54 mm (11 to 21 thou)
Pressure at tip: 12.6 to 19.6 MPa (1800 to 2800 psi)

CLEANING

Remove excess paint and clean all equipment using clean water immediately after use. Never store brushes or roller sleeves in water as this will result in deterioration of their application performance.

STORAGE & SHELF LIFE

Store unused paint in a cool, dry, frost free area away from direct sunlight. Ensure tin lids are securely and correctly replaced after use. When unopened and stored under the conditions above, this product is stable for a minimum period of two years.

DISPOSAL & RECYCLING

Dispose of excess or waste paint via a licensed waste handing operator.
Empty metal containers may be recycled (remove plastic handle on 2.5L tins).

HEALTH & SAFETY

Always read the label on the can before use. Ensure maximum ventilation during application and drying. Consult product material safety data sheet for further details.

Disclaimer - The information on this data sheet is correct to the best of our knowledge and experience. The Little Greene Paint Company reserves the right to modify data contained herein, without notice. The information supplied does not absolve users from responsibility to carry out their own tests and experiments, not does it imply any legally binding assurance of certain properties or suitability for any specific purpose. Conditions of service and application may be beyond our control, so no liability whatsoever can be accepted on the basis of the information supplied herein.

The Little Greene Paint Company Limited, The Coach Works, 420 Ashton Old Road, Manchester M11 2DT, England.
Tel: 0845 880 5855 (UK) Tel: +44 161 23 00 880 (Overseas) Fax: 0845 880 5877 (UK) Fax: +44 161 22 33 208 (Overseas)
mail@littlegreene.com www.littlegreene.com